

## > INDUSTRY BULLETIN

# Versaflex<sup>™</sup> & Versalloy<sup>™</sup> Specialty Engineered Materials Thermoplastic Elastomers for Healthcare Applications

Delivering specialized thermoplastic elastomer (TPE) solutions for demanding healthcare applications, Avient has performance-grade materials that are approved for USP VI, ISO 10993-4 and 10993-5. Formulated without phthalate plasticizers, several of our grades offer high clarity, bond to a variety of substrates and can be customized. Additional specialty grades span a wide durometer range and are formulated without animal derivatives for use in a broad range of applications. Common healthcare applications include medical tubing, gaskets and stoppers, bags, bottles and films, grips, handles and medical devices.

#### VERSAFLEX<sup>™</sup> HC MEDICAL TUBING SERIES

- Improve extrusion rates, achieve high service temperature performance or increase clarity in medical tubing
- Meet biopharmaceutical needs for weldability and minimize extractables during processing

#### VERSAFLEX<sup>™</sup> HC GASKETS & STOPPERS SERIES

- Achieve no coring, good puncture and resealability in static stoppers
- Meet low COF and low stiction requirements in dynamic seals

# VERSAFLEX<sup>™</sup> CL E SERIES

- Increase clarity and flexibility in bags, bottles and films
- Mitigate risk with plasticizer-free formulations for film extrusion
- Deliver excellent odor & O<sub>2</sub> barrier performance for film extrusion

### VERSALLOY<sup>™</sup> HC SERIES

- Obtain better flow in long, thin paths and lower shrink rates versus typical TPVs with our alloys, made with Santoprene<sup>™</sup> TPV
- Color easily and obtain a smooth tactile feel



# TPE HEALTHCARE PRODUCT SELECTOR GUIDE

	GENERAL PROPERTIES					TENSILE PROPERTIES									REGULATORY		OTHER
	Color	Hardness	Specific Gravity	Compression Set @ 23°C	Compression Set @ 100°C	100% Modulus		300% Modulus		Tensile Strength		Elongation	Tear Strength		ISO 10993	USP VI	Special Characteristics
		ASTM Shore A	ASTM/ISO	ASTM %	ASTM %	ASTM psi	Мра	ASTM psi	Мра	ASTM psi	ISO Mpa	ASTM %	ASTM pll	ISO kN/m			
Versaflex <sup>™</sup> HC MT Series																	
Versaflex <sup>™</sup> HC MT222	Clear	66A	0.88	14	-	334	2.30	629	4.34	898	6.19	430	220	36	~	~	
Versaflex <sup>™</sup> HC MT224	Clear	75A	0.89	19	-	468	3.23	773	5.33	1360	9.40	530	321	56	~	~	High clarity, without plasticizers
Versaflex <sup>™</sup> HC MT226	Clear	84A	0.88	20	-	606	4.17	885	6.10	1600	11.00	600	433	76	~	~	
Versaflex <sup>™</sup> HC MT317	Clear	68A	0.89	17	69	450	3.10	660	4.55	870	6.00	470	221	39	~	~	Very high service temperature
Versaflex <sup>™</sup> HC BT218	Natural	67A	0.89	19	69	381	2.60	683	4.70	1186	8.20	608	-	-	~	~	Weldable, kink resistant
Versaflex <sup>™</sup> HC Gaskets & Ste	oppers Series																
Versaflex <sup>™</sup> HC 2110-35N	Natural	34A	0.90	19	47	145	1.00	261	1.80	400	2.76	620	97	17	~	~	Good resealing
Versaflex <sup>™</sup> HC 2110-43N	Natural	43A	0.98	12	46	134	0.92	368	2.54	723	4.98	710	-	-	~	~	Good compression set
Versaflex <sup>™</sup> HC 2110-57B	Black	59A	1.01	20	37	369	2.54	558	3.85	537	3.70	350	147	26	~	~	Low stiction
Versaflex <sup>™</sup> CL E Series																1	
Versaflex <sup>™</sup> CL E85	Clear	84A	0.90	20	72	752	5.18	1160	8.00	1550	10.70	450	433	76	~	<ul> <li>✓</li> </ul>	High clarity, without plasticizers; E95 also offers excellent odor & O <sub>2</sub> barrier
Versaflex <sup>™</sup> CL E90	Clear	90A	0.90	27	73	1000	6.89	1230	8.50	1830	12.60	57	-	-	~	~	
Versaflex <sup>™</sup> CL E95	Clear	95A	0.90	38	71	1680	11.60	1730	11.90	2500	17.20	580	720	126	~	~	
Versaflex <sup>™</sup> HC 3810 Series				1													
Versaflex <sup>™</sup> HC 3810-20N	Natural	20A	0.88	16	54	123	0.80	185	1.30	342	2.40	650	-	-	~	-	Formulated without animal derivatives, excellent colorability, translucent
Versaflex <sup>™</sup> HC 3810-30N	Natural	30A	0.89	18	58	170	1.20	245	1.70	459	3.20	680	-	-	~	-	
Versaflex <sup>™</sup> HC 3810-40N	Natural	40A	0.88	19	59	191	1.30	275	1.90	506	3.50	670	-	-	~	-	
Versaflex <sup>™</sup> HC 3810-50N	Natural	50A	0.89	21	61	264	1.80	366	2.50	699	4.80	690	-	-	~	-	
Versaflex <sup>™</sup> HC 3810-60N	Natural	60A	0.88	24	65	459	3.20	594	4.10	790	5.40	510	-	-	~	-	
Versaflex <sup>™</sup> HC 3810-70N	Natural	70A	0.88	28	67	535	3.70	684	4.70	1000	6.90	570	-	-	~	-	
Versaflex <sup>™</sup> HC 3810-80N	Natural	80A	0.88	30	67	689	4.80	869	6.00	1390	9.60	620	-	-	~	-	
Versaflex <sup>™</sup> HC 3810-90N	Natural	90A	0.88	27	89	1087	7.50	1350	9.30	1890	13.00	570	-	-	~	-	
Versalloy <sup>™</sup> HC 9210 Series							1										
Versalloy <sup>™</sup> HC 9210-45N	Natural	45A	0.89	19	39	160	1.10	320	2.20	484	3.33	480	100	18	-	~	
Versalloy <sup>™</sup> HC 9210-55N	Natural	53A	0.89	20	44	208	1.44	335	2.31	580	4.00	610	120	21	-	V	Smooth surface aesthetics
Versalloy <sup>™</sup> HC 9210-70N	Natural	70A	0.89	23	53	356	2.45	510	3.52	780	5.38	590	180	32	-	~	
Versalloy <sup>™</sup> HC 9220 Series		-		-										-			
Versalloy <sup>™</sup> HC 9220-70	Natural	70A	0.95	17	51	453	3.12	-	-	643	4.43	265	208	36	~	<ul> <li>✓</li> </ul>	
Versalloy <sup>™</sup> HC 9220-80	Natural	80A	0.94	18	59	553	3.67	777	5.36	945	6.52	415	208	36	~		Extrudable
Versalloy <sup>™</sup> HC 9220-90	Natural	90A	0.94	25	55	1030	8.13	1350	9.33	1945	13.45	620	400	70	~	~	
Standard Healthcare Grade		30/1	0.51	25		1030	0.15	1000	5.55	1313	13.15	020	100	10		•	
Versaflex <sup>™</sup> G2705N	Natural	60A	0.88					528	3.64	670	4.62	470			~	~	Natural, high strength
Versaflex <sup>™</sup> CL 2242	Clear	43A	0.88	23	-	- 152	- 1.05	294	2.02	731	5.00	780	- 124	- 22			Natural, high strength
Versaflex <sup>™</sup> CL 2242	Clear	43A 50A	0.89	23	-	220	1.05	337	2.02	827	5.00	780	124	25			High clarity, boilable
	Ciedi		0.09		-	220	1.32	331	2.32	021	5.10	110	140	23			
Versaflex <sup>™</sup> OM Series																	
Versaflex <sup>™</sup> OM 1040X	Natural	42A	0.92	22	-	180	1.24	301	2.08	504	3.47	580	100	18	~	V	ABS/PC overmold
Versaflex <sup>™</sup> OM 3060	Clear	59A	0.90	33	-	420	2.90	360	2.48	500	3.45	480	180	32	~	<ul> <li>✓</li> </ul>	



#### www.avient.com



Copyright © 2020, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABLITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information, or inducement to practice any patented invention without permission of the patent owner.